

TENARIS.010A2


DELPHION[Select CR](#)**RESEARCH****PRODUCTS****INSIDE DELPHION**[Log Out](#)[Work Files](#)[Saved Searches](#)[My Account](#)Search: [Quick/Number](#) [Boolean](#) [Advanced](#) [Derwent](#)[Help](#)

The Delphion Integrated View

Get Now: ☒ PDF | [File History](#) | [Other choices](#)Tools: Add to Work File: [Create new Work File](#) [Add](#)View: [INPADOC](#) | Jump to: [Top](#) Go to: [Derwent](#)[Email this to a friend](#)**Title: JP63004047A2: HIGH-TENSILE STEEL FOR OIL WELL EXCELLENT IN SULFIDE CRACKING RESISTANCE****Derwent Title:** Sulphide corrosion resistant, high strength steel for oil well - contains carbon, silicon, manganese, chromium, molybdenum, titanium, aluminium, boron, zirconium etc. [[Derwent Record](#)]**Country:** JP Japan**Kind:** A DOC. LAID OPEN TO PUBL. INSPEC. [PUBLISHED FROM 1971 ON] ¹**Inventor:** KANEKO TERUO;
IKEDA AKIO;**Assignee:** SUMITOMO METAL IND LTD
[News, Profiles, Stocks and More about this company](#)**Published / Filed:** 1988-01-09 / 1986-06-20**Application Number:** JP1986000145915**IPC Code:** Advanced: [C22C 38/00](#); [C22C 38/54](#);
Core: [more...](#)
IPC-7: [C22C 38/00](#); [C22C 38/54](#);**Priority Number:** 1986-06-20 JP1986000145915**Abstract:** PURPOSE: To obtain a high-tensile steel for oil well excellent in sulfide cracking resistance by specifying a composition consisting of C, Si, Mn, Cr, Mo, Ti, Al, B, Zr, Hf, Nb, V, and Fe and by properly limiting the amounts of inevitable- impurity elements.

CONSTITUTION: The high-tensile steel for oil well excellent in sulfide cracking resistance has a composition which consists of, by weight, 0.15W0.45% C, 0.1W0.8% Si, 0.2W0.8% Mn, 0.2W<1.0% Cr, 0.1W0.8% Mo, 0.001W<0.010% Ti, 0.005W0.060% Al, 0.0001W0.0030% B, 0.01W0.15% Zr and/or 0.001W0.150% Hf, 0.01W0.15% Nb and/or 0.01W0.15% V, and the balance essentially Fe and further containing, if necessary, one or more kinds among 0.001W0.010% Ca and 0.001W0.030% rare earth elements and in which amounts of P, S, Cu, Ni, N, and O among inevitable impurities are limited to ≤0.01%, ≤0.005%, ≤0.15%, ≤0.05%, ≤0.0150%, and ≤0.0050%, respectively and, moreover, it is free from deterioration due to plastic deformation.

COPYRIGHT: (C)1988,JPO&Japio

Family: None**Other Abstract Info:** [CHEMABS 108\(18\)154557X](#) [CAN108\(18\)154557X](#) [DERABS C88-046359](#) [DERC88-046359](#)[Nominate this for the Gallery...](#)

Copyright © 1997-2009 Thomson Reuters

[Subscriptions](#) | [Web Seminars](#) | [Privacy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)